

### CERTIFICATE OF ANALYSIS

**CUSTOMER**

Polygiene AB  
Stadiongatan 65  
SE-217 62 Malmö  
SWEDEN

**CERTIFICATE NO.**

1013627.49/4510

**CUSTOMER REF.**

PG346

**SAMPLE DETAILS**

DENBER PAINTS + COATINGS ISRAEL LTD

**DATE RECEIVED**

01/04/2010

**ORDER NO.**

**METHOD: Determination of Antibacterial Activity using Test Based on MOD JIS Z 2801:2000**

**DATE ANALYSED**

07/04/2010

**DATE REPORTED**

09/04/2010

**RESULTS (AS CFU CM<sup>-2</sup>)**

SAMPLE	SPECIES	CONTACT TIME		REDUCTION (INITIAL)	
		0 hrs	24 hrs	Log 10	%
DENBERGLOSS FLOOR 100% SOLID PAINT	<i>E coli</i>	2.0E+04	< 11.11	≥ 3.26	≥ 99.94%
DENBERGLOSS FLOOR 100% SOLID PAINT	<i>E coli</i>	2.0E+04	1.1E+06		
DENBERGLOSS FLOOR 100% SOLID PAINT	MRSA	2.4E+04	< 11.11	≥ 3.33	≥ 99.95%
DENBERGLOSS FLOOR 100% SOLID PAINT	MRSA	2.4E+04	5.1E+02		

בדיקה של פוליוג'ן על כלים 100% מוליטיים

במקרה של פוליוג'ן.

Key: NS = Poor survival on control supplied.

The above data shows the difference in the population following contact with the surface of the samples listed for 24 hours at 35°C under a RH of > 95% relative to the initial population.

IMSL MICROBIOLOGICAL SERVICES LTD  
PALE LANE  
HARTLEY WINTNEY  
HANTS RG27 8DH  
UK

MANAGING DIRECTOR  
Peter D Askew

### CERTIFICATE OF ANALYSIS

Page 1 of 1

#### CUSTOMER

Polygiene AB  
Stadiongatan 65  
SE-217 62 Malmö  
SWEDEN

CERTIFICATE NO.

1013627.55/4515

CUSTOMER REF.

PG346

#### SAMPLE DETAILS

DENBER PAINTS + COATINGS ISRAEL LTD

DATE RECEIVED

01/04/2010

ORDER NO.

METHOD: Determination of Antibacterial Activity using Test Based on MOD JIS Z 2801:2000

DATE ANALYSED

07/04/2010

DATE REPORTED

09/04/2010

#### RESULTS (AS CFU CM<sup>-2</sup>)

SAMPLE	SPECIES	CONTACT TIME		REDUCTION (INITIAL)	
		0 hrs	24 hrs	Log 10	%
BACTERINOLL PAINT	<i>E coli</i>	2.0E+04	< 11.11	≥ 3.26	≥ 99.94%
BACTERINOLL PAINT	<i>E coli</i>	2.0E+04	1.1E+06		
BACTERINOLL PAINT	MRSA	2.4E+04	< 11.11	≥ 3.33	≥ 99.95%
BACTERINOLL PAINT	MRSA	2.4E+04	5.1E+02		

דביר דביר  
דביר דביר

Key: NS = Poor survival on control supplied.

The above data shows the difference in the population following contact with the surface of the samples listed for 24 hours at 35°C under a RH of > 95% relative to the initial population.

IMSL MICROBIOLOGICAL SERVICES LTD  
PALE LANE  
HARTLEY WINTNEY  
HANTS RG27 8DH  
UK

MANAGING DIRECTOR  
Peter D Askew