



Test Report

No. CANFD1214938101

Date: 12 Nov 2012

Page 1 of 3

The following sample(s) was/were submitted and identified on behalf of the clients as : ADDITION CURE SILICONE RUBBER

Date of Sample Received : 06 Nov 2012
Testing Period : 06 Nov 2012 - 12 Nov 2012
Test Requested : Selected test(s) as requested by client.
Test Method : Please refer to next page(s).
Test Results : Please refer to next page(s).

Result Summary :

Test Requested		
FDA 21 CFR 177.2600-Total extractive residues		PASS

Conclusion : When tested as specified, the tested parameters comply with the requirement stating under Food and Drug Administration Regulations.

Signed for and on behalf of
SGS-CSTC Ltd.

Jenny Jiang
Approved Signatory





Test Report

No. CANFD1214938101

Date: 12 Nov 2012

Page 2 of 3

Test Results :

Test Part Description :

Specimen No.	SGS Sample ID	Description
1	CAN12-149381.001	Translucent silicone rubber sheet

FDA 21 CFR 177.2600—Total extractive residues

Test Requested : As specified by client, to determine total extractive residues from Rubber articles intended for repeated use in contact with food for compliance with Food and Drug Administration Regulations.

Test Method : With reference to US FDA 21 CFR 177.2600.

<u>Simulant Used</u>	<u>Time</u>	<u>Temperature</u>	<u>Max. Permissible Limit</u>	<u>Result of 001</u>	<u>Comment</u>
Distilled Water	7.0hr(s)	Reflux temperature	20mg/sq. in	0.6mg/sq. in	PASS
Succeeding Extraction	2.0hr(s)	Reflux temperature	1mg/sq. in	<0.5mg/sq. in	PASS
n-Hexane	7.0hr(s)	Reflux temperature	175mg/sq. in	23.2mg/sq. in	PASS
Succeeding Extraction	2.0hr(s)	Reflux temperature	4mg/sq. in	2.1mg/sq. in	PASS

Notes :

mg/inch²= milligram per square inch


Test Report

No. CANFD1214938101

Date: 12 Nov 2012

Page 3 of 3

Sample photo:



SGS authenticate the photo on original report only

*** End of Report ***